

KANTHAL

Data Sheet	KANTHAL 155C Thermostatic bimetal	1995-04-10 Issue 1
-------------------	--	-------------------------------------

KANTHAL 155C is a thermostatic bimetal which is recommended for use in the temperature range -20 to +350°C. In extreme cases it can be used at temperatures up to a maximum of +450°C.

Typical applications for KANTHAL 155C are in circuit breakers, motor protection units, thermostats, shower mixers, etc.

General

	Alloy	Designation	Portion of thickness %
High-expansive component	15-7 C	441	50
Low-expansive component	Invar 155	450	50
Intermediate component		-	-

Chemical composition

	Designation	C %	Mn %	Ni %	Fe %
High-expansive component	441	0.50	6.9	17.0	Balance
Low-expansive component	450	-	0.12	36.8	Balance

Mechanical properties

Components	Designation	Hardness Hv	
High-expansive component	441	-	Annealed
Low-expansive component	450	-	Annealed

Bimetal	Designation	Hardness Hv	
High-expansive component	441	260	Cold-worked 20 %
Low-expansive component	450	210	Cold-worked 20 %

Young's modulus

Temperature °C	20
x 10 ³ MPa	170

KANTHAL is a registered trade mark of Kanthal AB in Sweden and other countries.

Kanthal AB reserves the right to change the contents of this document without notification to holders of prior issues of the same.

The data given are representative for the product. Kanthal will not guarantee any values, except when maximum or minimum values are explicitly stated.

Data Sheet	KANTHAL 155C Thermostatic bimetal	1995-04-10 Issue 1
------------	--------------------------------------	-----------------------

Physical properties

Density g/cm^3 8.1

Electrical resistivity

	Designation	Temperature $^{\circ}\text{C}$	0	20	100	200	300	400
Bimetal	155C	$\text{mm}^2 \text{m}^{-1}$	0.77	0.78	0.86	0.94	1.00	1.07
High-expansive component	441	$\text{mm}^2 \text{m}^{-1}$		0.80				
Low-expansive component	450	$\text{mm}^2 \text{m}^{-1}$		0.79				

Coefficient of thermal expansion

	Designation	Temperature $^{\circ}\text{C}$	Thermal Expansion $\times 10^{-6} \text{K}^{-1}$
High-expansive component	440	35 - 120	19.4
Low-expansive component	450	35 - 120	0.5

Specific deflection $\times 10^{-6} \text{K}^{-1}$ 15.6

Specific thermal curvature $\times 10^{-6} \text{K}^{-1}$ 28.5

Linearity range $^{\circ}\text{C}$ -20 to +250

Thermal conductivity

Temperature $^{\circ}\text{C}$	20
$\text{W m}^{-1} \text{K}^{-1}$	13

Specific heat capacity

Temperature $^{\circ}\text{C}$	20
$\text{kJ kg}^{-1} \text{K}^{-1}$	0.46

Temperature range $^{\circ}\text{C}$ -20 to +350

Maximum operating temperature $^{\circ}\text{C}$ +450

Marking on the high expansion side 155TB1577B